



FEATURES

: SEAGUARD is a tin free antifouling paint with polishing action in service and long protection against marine organisms. The specific vehicle composition provides long lasting performance and polishing action.
: As an antifouling paint on steel ship's bottom for world wide service with service with extended drydocking interval.

TECHNICAL INFORMATION

Type : Self-polish anti-fouling paint
Color : Light Red, Dark Red
Film appearance : Matt
Specific gravity : 1.85 ± 0.05
Solid by volume : $44 \pm 2 \%$
Flash point : $17 \text{ }^\circ\text{C}$

		Minimum	Maximum	Recommended
Dry film thickness	(Microns)	75	150	75
Wet film thickness	(Microns)	170	341	170
Theoretical coverage.	m ² / Liter	5.9	2.9	5.9
	m ² / Gallon	22.2	11.1	22.2
Practical coverage.	m ² / Liter	5.3	2.6	5.3
	m ² / Gallon	20.0	10.0	20.0

Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

	Temperature	25 °C	30 °C	35 °C
Touch dry	Surface dry	2 hrs.	1 hr.	30 mins.
	Hard dry	8 hrs.	5 hrs.	4 hrs.
Recoat dry	Minimum	8 hrs.	5 hrs.	4 hrs.
	Maximum	18 hrs.	12 hrs.	10 hrs.

Remark : Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

APPLICATION

	Mixing Ratio	Part A	Part B	
	By Volume	1	-	
	By Weight	1	-	
Application Method		Airless Spray	Air Spray	Brush / Roller
Diluted by		5-10	15-20	10-15
	TOA Thinner 51			
Applicator		Graco 621	Coventional Spray (Iwata)	Short Hair Stiff Nylon Roller (Stanley)
		Graco 623		Stiff Nylon Brush
Pressure		120-150 kg/cm ²	3-4 kg/cm ²	-

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.



APPLICATION INFORMATION

Surface Preparation

Steel

: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project.

Remark : The surface must be thoroughly dry and apply the protective coating within 4 hours to cleaned surface.

Before Recoat by Topcoat

: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.

: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.

: Surface repaire (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.

Coating System

Protective protective Coating

: Primer	Coal Tar Epoxy # 111	125 microns x 2 coats
: Undercoat	Tieguard	40 microns x 1 coat
: Topcoat	Seaguard	75 microns x 2 coats

Recommendation

: The proper relative humidity in the work shall not exceed 85% RH.

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air , temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

Shelf life

: 24 months at 30-35 °C

Package

Packaging size

1 Gallon Set

1 Gallon

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.