SILGUARD 400

## **Technical Data Sheet**



					Rev. 1 10/20	
FEATURES						
	: Silguard 400 is	: Silguard 400 is a silicone resin.				
	: As a excellent heat resistance to temperature up to 400 $^\circ$ C for boiler, exhaust pipe, oil burner.					
TECHNICAL INFORMATION						
Туре	: Silicone heat re	: Silicone heat resisting paint				
Color	: Silver (No.333) and Black (N0. 999)					
Film appearance	: Matt					
Specific gravity	: 1.20 <u>+</u> 0.05					
Solid by volume	: 35 <u>+</u> 2 %					
Flash point	: 27 °C					
		Minimum	Maximum	Recommended		
Dry film thickness	(Microns)	15	30	15		
Wet film thickness	(Microns)	43	86	43		
Theoretical coverage.	m <sup>2</sup> / Liter	23.3	11.7	23.3		
	m <sup>2</sup> / Gallon	88.3	44.2	88.3		
Practical coverage.	m <sup>2</sup> / Liter	21.0	10.5	21.0		
	m <sup>2</sup> / Gallon	80.0	40.0	80.0		
	Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition					
	method and technique; as well as the structure and dimensions of the object to be coated.					
	Temperature	25 °C	30 °C	35 °C		
Touch dry	Surface dry	25 mins	20 mins	15 mins		
Recoat dry	Hard dry	1.5 hrs.	1 hr.	45 mins		
Full cure	Minimum	10 hrs.	8 hrs.	6 hrs.		
	Maximum	-	_	-		
		times are genera	lly related to air circula	tion, temperature, film	thickness and number	
		Il be affected corr	-	tion, temperature, nim		
APPLICATION						
	Mixi	ng Ratio	Part A	Part B		
		By Volume		-		
	By Weight		1	_		
		By Weight				
	Application Method		Airless Spray	Air Spray	Brush / Roller	
		Diluted by		15-20	10-15	
	ΤΟΑ Τ	TOA Thinner 91				
			Graco 415	Coventional Spray	Short Hair Stiff Nylo	
	Apr	Applicator		(Iwata)	Roller (Stanley)	
			Graco 417		Stiff Nylon Brush	
	Pressure		90-120 kg/cm <sup>2</sup>	3-4 kg/cm <sup>2</sup>	-	

**SILGUARD 400** 



Rev. 1 10/2017

APPLICATION SYSTEM					
Surface Preparation					
<u>Steel</u>	: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project. <i>Remark</i> : The surface must be thoroughly dry and apply the protective coating within 4 hours				
Before Recoat by Topcoat	<ul> <li>to cleaned surface.</li> <li>: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.</li> <li>: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.</li> <li>: Surface repaire (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.</li> </ul>				
Coating System					
Protective Coating	: Primer & Topcoat Silguard 400 15 microns x 2 coats				
Recommendation	<ul> <li>The proper relative humidity in the work shall not exceed 85% RH.</li> <li>The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.</li> </ul>				
HANDLING AND STORAGE					
Storage condition	: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.				
Shelf life	: 24 months at 30-35 °C				
Package	Packaging size 1 Gallon Set 1 Gallon				
HEALTH AND SAFETY	<ul> <li>Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.</li> <li>For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.</li> </ul>				
DISCLAIMER					
	: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.				