SILGUARD 200

## **Technical Data Sheet**



FEATURES					
	: Silguard 200 is	a heat resistance	e paint, base on silicone	e resin, modified with a	crylic resin.
	: As a excellent heat resistance to temperature up to 250 °c for steam pipe, high temperature parts.				
TECHNICAL INFORMATION					
	: Silicone Acrylic heat resisting paint				
Type Color	: Silicone Acrylic heat resisting paint : Silver (No.333) and Black (NO. 999)				
	: Silver (No.333) and Black (No. 999) : Matt				
Film appearance	-				
Specific gravity	: 1.20 <u>+</u> 0.05				
Solid by volume	: 40 <u>+</u> 2 % : 23 <sup>°</sup> C				
Flash point	: 23 0	N 4 ive i vers	Massimerum	Decembranded	
		Minimum	Maximum	Recommended	
Dry film thickness	(Microns)	15	30	15	
Wet film thickness	(Microns)	38	75	38	
Theoretical coverage.	m² / Liter	26.7	13.3	26.7	
	m <sup>2</sup> / Gallon	100.9	50.5	100.9	
Practical coverage.	m <sup>2</sup> / Liter	24.0	12.0	24.0	
	m <sup>2</sup> / Gallon	91.0	45.0	91.0	
	Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Conditio				
	method and technique; as well as the structure and dimensions of the object to be coated.				
	Temperature	25 °C	30 °C	35 °C	
Touch dry	Surface dry	50 mins	30 mins	20 mins	
Recoat dry	Hard dry	3 hrs.	2 hrs.	1 hr.	
Full cure	Minimum	10 hrs.	8 hrs.	6 hrs.	
	Maximum	_	_	_	
	Remark : Drying	times are genera	Ily related to air circula	tion, temperature, film	thickness and numbe
		Il be affected corr	-	<i>,</i> , <i>,</i> ,	
APPLICATION	Mixir	na Patio	Part A	Part B	
	Mixing Ratio		Part A	Fart D	
	By Voulme		1	-	
	By Weight		1	-	
	Application Method		Airless Spray	Air Spray	Brush / Roller
	Diluted by		5-10	15-20	10-15
	TOA Thinner 91		3-10	13-20	10-15
			Graco 415	Covertienal Creak	Short Hair Stiff Nylc
	Apr	Applicator		Coventional Spray (Iwata)	Roller (Stanley)
				(iwata)	Stiff Nylon Brush
	Pressure		90-120 kg/cm <sup>2</sup>	3-4 kg/cm <sup>2</sup>	-

**SILGUARD 200** 



Rev. 1 10/2017

APPLICATION SYSTEM					
Surface Preparation					
<u>Steel</u>	: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project. <i>Remark</i> : The surface must be thoroughly dry and apply the protective coating within 4 hours				
	to cleaned surface.				
Before Recoat by Topcoat	: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.				
	<ul> <li>: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.</li> <li>: Surface repaire (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.</li> </ul>				
Coating System					
Protective Coating	: Primer & Topcoat Silguard 200 15 microns x 2 coats				
Recommendation	<ul> <li>The proper relative humidity in the work shall not exceed 85% RH.</li> <li>The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.</li> </ul>				
HANDLING AND STORAGE					
Storage condition	: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.				
Shelf life	: 24 months at 30-35 °C				
Package	Packaging size				
	1 Gallon Set 1 Gallon				
HEALTH AND SAFETY					
	<ul> <li>Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.</li> <li>For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.</li> </ul>				
DISCLAIMER					
	: The information in this data sheet is given to the best of our knowledge based on laboratory testing				
	and practical experience. However, as the product is often used under conditions beyond our control,				
	we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.				