**Wood Coating** Page: 1 **TOA** 

Topcoat

## SUPERSHIELD TIMBERSHIELD

## **Technical Data Sheet**



	Rev.1 10/2017
FEATURES	
	Supershield Timbershield is high sheen waterbase acrylic emulsion paint for exterior wood substrate. It composes of premium grade acrylic copolymer, high durable pigments and special additives. The properties of this product are self-cleaning, excellent weathering resistance, good waterproof, anti-fungi, high flexibility, good adhesion and good yellowing resistance.
TECHNICAL INFORMATION	
Туре	ACRYLIC EMULSION
Color	Wide range of colors. Please ask for catalog or fandeck.
Film appearance	Sheen
Solid by volume	68.0 ± 2.0 %
Solid by weight	53.0 ± 2.0 %
Flash point	- °C
Volatile organic compounds (VOCs)	27.6064 gram / liter
Wet film thickness	100 microns
Dry film thickness	50-60 microns
Theoretical coverage.	35-40 sq.m. / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition
	method and technique; as well as the structure and dimensions of the object to be coated.
Touch dry (25-30°C)	30-40 minutes.
Recoat dry (25-30°C)	1 hours.
Full cure (25-30°C)	1 days.
REFERENCE STANDARD	TIS No. 2321-2549 Thai Industrial Standard for Weather resistance Emulsion paint.
	Green Label (Thai Green Labek Scheme).
APPLICATION	
Tools	: Roller, Brush
Thinner No.	: Clean Water
Dilution (%)	: 5 – 10% by volume
APPLICATION SYSTEM	
Surface Preparation	
New surface	: TOA 301 Acrylic Sealent or TOA Acrylic Filler is used to repair all cracks and holes.
	: Use TOA Abrasive Paper to sand the wood surface until smooth.
	: The surfaces must be clean and free of dirt, grease, oil, wax, salt and other contaminants.
Old surface	: The surfaces must be clean and free of dirt, wax, salt, old paint and other contaminants.
	: Use TOA Abrasive Paper to sand the wood surface until smooth
	:TOA 301 Acrylic Sealent or TOA Acrylic Filler is used to repair all cracks and rough surfaces.
	: Sand again until the smooth surface is obtained and then clean the surface until no dust remain.
Coating system	
Primer	: Apply by brush or roller with TOA Aluminium Wood Primer#0AWP 1 coat (Recoatable at least 4 hr)
	: Apply by brush or roller with TOA Univarsal Undercoat White#G1600 1 coat(Recoatable at least 1 hr)

: Apply by brush or roller with SuperShield Timbershield at least 2 coats.

TOA

Wood Coating | Page : 2

## **Technical Data Sheet**



## SUPERSHIELD TIMBERSHIELD

	Rev.1 10/2017
	: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of
Recommendation	the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation
	is required in confined areas to ensure correct drying.
HANDLING AND STORAGE	· · ·
Storage condition	: The product must be stored in accordance with national regulations.
Storage condition	Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
	Containers must be kept tightly closed.
Shelf life	: 5 years. (at 25–30°C from manufacturing date)
HEALTH AND SAFETY	
HEALIH AND SAFETT	Places observe the proceditionary nations displayed on the container. He under well ventilated
	: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately
	be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and
	medical attention sought immediately.
	: For detailed information on the health and safety hazards and precautions for use of this product,
	we refer to the Material Safety Data Sheet.
DISCLAIMER	
DIOCE TIME!	: The information in this data sheet is given to the best of our knowledge based on laboratory testing
	and practical experience. However, as the product is often used under conditions beyond our control,
	we cannot guarantee anything only the quality of the product itself. We reserve the right to change
	the given data without notice.