MD CONTACT PRIMER

Technical Data Sheet



Rev.1 10/2017

FE	ΑΤΙ	JR	ES
ГС	\sim 1 $^{\circ}$	JN	EO

MD Contact Primer is based on 100% acrylic resin that designed to improve adhesion of new paint onto chalky surfaces or painted surfaces. The properties of this primer are good penetration and provide a strong bond between the painted surface and new paint.

TECHNICAL INFORMATION

Type : Acrylic Resin

Color : Clear
Film appearance : Gloss

Solid by volume $: 8.0 \pm 0.5$ % Solid by weight $: 10.0 \pm 0.5$ % Flash point : 39.0 °C

Volatile organic compounds (VOCs) : - gram / liter
Wet film thickness : 100 microns

Dry film thickness : 13-15 microns

Theoretical coverage. : 28-32 sq.m. / gallon / coat

: -

Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

 Touch dry (25-30°C)
 : 20-30
 minutes.

 Recoat dry (25-30°C)
 : 2
 hours.

 Full cure (25-30°C)
 : 1
 days.

REFERENCE STANDARD

APPLICATION

Tools : Roller, Brush
Thinner No. : Ready to use
Dilution (%) -

APPLICATION SYSTEM

Surface Preparation

Old surface : The surfaces must be clean and free of dirt, wax, salt, old paint and other contaminants.

: Chalky surfaces or loose material must be removed by stiff brush.

: TOA113 Microkill is used to get rid of algae and fungi that left on the surfaces.

: The surfaces must be clean with suitable cleansing solution and water then rinse thoroughly with fresh water and allow to fully dry.

: TOA 301 Acrylic Sealent or TOA Acrylic Filler is used to repair all cracks and rough surfaces.

Coating system

Primer : Apply by brush with MD Contact Primer 1 coat.

Topcoat : Can be topcoat with Acrylic Emulsion Paint and Alkyd Base Enamel Paint.

Recommendation : The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation

is required in confined areas to ensure correct drying.

Home & Building | Page : 2 TOA **MD CONTACT PRIMER**

Technical Data Sheet



	Rev.1 10/20
HANDLING AND STORAGE	
Storage condition	: The product must be stored in accordance with national regulations.
	Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.
Shelf life	Containers must be kept tightly closed. : 5 years. (at 25-30°C from manufacturing date)
	. o yours. (at 20 00 0 from manufacturing date)
HEALTH AND SAFETY	: Please observe the presquitionary notices displayed on the container. He under well ventilated
	: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediate
	be removed with s uitable cleanser, soap and water. Eyes should be well flushed with water and
	medical attention sought immediately.
	: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.
DISCLAIMER	
	: The information in this data sheet is given to the best of our knowledge based on laboratory testing
	and practical experience. However, as the product is often used under conditions beyond our control
	we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.