



<b>FEATURES</b>	SHARK Lacquer Sanding Sealer # S-5555 is based on Nitrocellulose Resin and designed to use as a primer for interior wood coating. Properties of the products are high film built, fast dry, easy to sand and good adhesion on solid wood and plywood.
<b>TECHNICAL INFORMATION</b>	<p>Type Nitrocellulose Lacquer</p> <p>Color Clear</p> <p>Film appearance Semi-Gloss</p> <p>Solid by volume NA</p> <p>Solid by weight 34.0 ± 2.0 %</p> <p>Flash point 15.3 °C</p> <p>Wet film thickness 100 microns</p> <p>Dry film thickness 35 microns</p> <p>Theoretical coverage. 40 - 45 m<sup>2</sup> / gallon / coat</p> <p>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.</p> <p>Touch dry ( 25-30°C) 5 - 10 minutes.</p> <p>Recoat dry ( 25-30°C) 20 minutes. (minimum)</p> <p>Full cure ( 25-30°C) 3 - 4 hours</p>
<b>REFERENCE STANDARD</b>	-
<b>APPLICATION</b>	<p>Tools Brush, Spray</p> <p>Thinner No. Barco Thinner #AAA</p> <p>Dilution (%) 100 - 150 % ( brush ) 100 - 200 % ( spray )</p>
<b>APPLICATION SYSTEM</b>	<p><b>Surface Preparation</b></p> <p><b>Old surface</b></p> <ol style="list-style-type: none"> <li>1. Chalky surfaces or loose material must be removed by stiff brush.</li> <li>2. The surfaces must be clean and free of dirt, wax, salt, old paint and other contaminants.</li> </ol> <p><b>New surface</b></p> <ol style="list-style-type: none"> <li>1. Use TOA abrasive paper no. 240 - 320 to sand the wood surface until smooth.</li> <li>2. Fill all wood crack and hole by filler.</li> <li>3. Sand again until the smooth surface is obtained.</li> <li>4. The surfaces must be clean and free of dirt, grease, oil, wax, salt and other contaminants.</li> </ol> <p><b>Coating system</b></p> <p><b>Primer</b></p> <p>Apply by brush or spray with SHARK Lacquer Sanding Sealer # S-5555 at least 2 coats. (Recoat time is at least 20 minutes)</p> <p><b>Topcoat</b></p> <ol style="list-style-type: none"> <li>1. Apply by brush or spray with SHARK Lacquer Gloss or Matt at least 2 coats.</li> <li>2. Before topcoat any layer, TOA abrasive paper no. 320 - 400 are recommended to sand the surface which provide good intercoat adhesion and smooth the surface.</li> </ol> <p>Remark - DO NOT use SHARK Lacquer Sanding Sealer # S-5555 as a primer for Polyurethane because of poor intercoat adhesion or peeling problem.</p>



<b>Recommendation</b>	: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.
<b>HANDLING AND STORAGE</b>	
<b>Storage condition</b>	: The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.
<b>Shelf life</b>	: 2 years (from manufacturing date)
<b>HEALTH AND SAFETY</b>	
	: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. : For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.
<b>DISCLAIMER</b>	
	: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

คุณสมบัติ	สีรองพื้นปรับระนาบผิวและอุดเสี้ยนไม้ ตราปลาฉลาม # S-5555 ผลิตจากโพลีเอสเตอร์เรซิน เหมาะสำหรับใช้เป็นสีรองพื้นงานไม้ภายใน ห้องเร็ว ใช้งานง่าย จับฟิล์มไว สามารถยึดเกาะได้ดีบนไม้จริง และ ไม้อัดมีลายแบบต่างๆ
ข้อมูลทางเทคนิค	<p>ประเภทสี โพลีเอสเตอร์ แอ็กเกอร์</p> <p>ชนิดสี ใส</p> <p>ลักษณะฟิล์มสี กึ่งเงา</p> <p>เนื้อสีโดยปริมาตร ไม่มีข้อมูล</p> <p>เนื้อสีโดยน้ำหนัก 34.0 ± 2.0 %</p> <p>จุดควบไฟ 15.3 °C</p> <p>ความหนาฟิล์มสีเมื่อเปียก 100 ไมครอน</p> <p>ความหนาฟิล์มสีเมื่อแห้ง 35 ไมครอน</p> <p>การครอบคลุมพื้นที่ตามทฤษฎี 40 - 45 ตารางเมตร ต่อ แกลอน ต่อ เทียว</p> <p>หมายเหตุ : การผสม, การใช้งาน, ความหนายและอุณหภูมิของพื้นผิว มีผลต่อค่าการปกคลุมพื้นผิว</p> <p>ระยะเวลาแห้งสัมผัส (อุณหภูมิ 25-30°C) 5 - 10 นาที</p> <p>ระยะเวลาแห้งทาทับ (อุณหภูมิ 25-30°C) 20 นาที (เป็นอย่างน้อย)</p> <p>ระยะเวลาแห้งสมบูรณ์ (อุณหภูมิ 25-30°C) 3 - 4 ชั่วโมง</p>
มาตรฐานอ้างอิง	-
วิธีใช้งาน	<p>อุปกรณ์ แปรงทาสี เครื่องพ่น</p> <p>ทินเนอร์ ทินเนอร์ บราโก้ AAA</p> <p>การผสมทินเนอร์ (%) 100 - 150 % (ทา) 100 - 200 % (พ่น)</p>
ระบบการใช้งาน	<p>การเตรียมพื้นผิว</p> <p>พื้นผิวเก่า</p> <ol style="list-style-type: none"><li>ควรขัดสีเก่าที่เสื่อมสภาพหรือวัสดุต่างๆบนพื้นผิวเดิมออกก่อน</li><li>เช็ดทำความสะอาด พื้นผิวต้องปราศจากสิ่งสกปรก, คราบไขมัน, คราบเกลือ, สีเก่าและสารปนเปื้อนอื่นๆ</li></ol> <p>พื้นผิวใหม่</p> <ol style="list-style-type: none"><li>ใช้กระดาษทรายขัดแห้ง ทีโอเอ ดือสซี #240 - 320 ขัดแต่งพื้นผิวจนเรียบสวย</li><li>อุดโป๊วรอยแตก ตำหรับไม้และหิวตะปู ให้เรียบร้อย</li><li>ขัดแต่งด้วยกระดาษทรายอีกครั้ง จนได้พื้นผิวที่เรียบเนียน</li><li>เช็ดทำความสะอาด พื้นผิวต้องปราศจากสิ่งสกปรก, คราบไขมัน, คราบเกลือและสารปนเปื้อนอื่นๆ</li></ol> <p>ระบบการทาสี</p> <p>สีรองพื้น</p> <p>ทาหรือพ่นรองพื้นด้วย สีรองพื้นปรับระนาบผิวและอุดเสี้ยนไม้ ตราปลาฉลาม # S-5555 อย่างน้อย 2 เทียว (ทิ้งให้แห้งอย่างน้อย 20 นาที ก่อนทา หรือ พ่นทับเที่ยวต่อไป)</p> <p>สีทับหน้า</p> <ol style="list-style-type: none"><li>ทาหรือพ่นด้วย แอ็กเกอร์ ตราปลาฉลาม ชนิดเงา หรือ ดำน อย่างน้อย 2 เทียว</li><li>ก่อนทาหรือพ่นทับหน้าเที่ยวต่อไป ให้ขัดแต่งพื้นผิวด้วยกระดาษทราย ทีโอเอ ดือสซี #320 - 400 เพื่อเพิ่มการยึดเกาะและได้พื้นผิวชั้นงานที่เรียบ</li></ol> <p>หมายเหตุ : ห้ามใช้เป็นสีรองพื้นสำหรับงานโพลีเอสเตอร์ เนื่องจากการยึดเกาะระหว่างชั้นของโพลีเอสเตอร์และโพลีเอสเตอร์ มีค่าต่ำมาก ซึ่งฟิล์มสีอาจลอกหลุดได้ง่าย</p> <p>ข้อแนะนำการปฏิบัติงาน</p> <p>: อุณหภูมิของชิ้นงานจะต้องสูงกว่า 10°C และสูงกว่าจุดน้ำค้างอย่างน้อย 3°C อุณหภูมิและความชื้นสัมพัทธ์ต่างมีผลต่อชิ้นงานและการแห้งตัวของฟิล์มสี</p>

## การเก็บรักษา

สภาวะการเก็บรักษา

: จัดเก็บสินค้าในที่แห้ง มีอากาศถ่ายเทดี ปิดฝาให้สนิท  
ให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนและไม่ให้ถูกแสงแดดโดยตรง

อายุผลิตภัณฑ์

: 2 ปี (นับจากวันที่ผลิต)

## ข้อมูลสุขภาพและความปลอดภัย

: กรุณาดูข้อควรระวังที่ติดไว้บนภาชนะบรรจุ การทำงานสีควรทำในที่อากาศถ่ายเทสะดวก  
ควรใส่หน้ากากเมื่อทำการพ่นสีและพยายามเลี่ยงมิให้สัมผัสผิวหนัง หรือสูดดม  
ถ้าสีหกใส่ผิวหนังควรล้างด้วยน้ำสะอาดกับสบู่ทันที ถ้าสีเข้าตาควรล้างด้วยน้ำสะอาดทันทีและรีบไปพบแพทย์  
: รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในข้อมูลด้านความปลอดภัย

## การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้  
ในสภาวะแตกต่างกันเราจึงไม่สามารถรับประกันในสิ่งอื่นใดนอกจากคุณภาพของสีเท่านั้น  
**บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิต้องแจ้งล่วงหน้า**