

FEATURES

- : Silguard 700 is a silicone resin
- : As a excellent heat resistance to temperature up to 700 °C for boiler, exhaust pipe, oil burner.

TECHNICAL INFORMATION

- Type : Silicone heat resisting paint
- Color : Silver (No.333) and Black (NO. 999)
- Film appearance : Matt
- Specific gravity : 1.20 ± 0.05
- Solid by volume : 34 ± 2 %
- Flash point : 27 °C

		Minimum	Maximum	Recommended
Dry film thickness	(Microns)	15	30	15
Wet film thickness	(Microns)	44	88	44
Theoretical coverage.	m ² / Liter	22.7	11.3	22.7
	m ² / Gallon	85.8	42.9	85.8
Practical coverage.	m ² / Liter	20.4	10.0	20.4
	m ² / Gallon	77.0	38.6	77.0

Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

	Temperature	25 °C	30 °C	35 °C
Touch dry	Surface dry	25 mins	20 mins	15 mins
	Hard dry	1.5 hrs.	1 hr.	45 mins
Full cure	Minimum	10 hrs.	8 hrs.	6 hrs.
	Maximum	-	-	-

Remark : Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

APPLICATION

Mixing Ratio	Part A	Part B	
By Volume	1	-	
By Weight	1	-	
Application Method	Airless Spray	Air Spray	Brush / Roller
	Diluted by TOA Thinner 91	5-10	15-20 10-15
Applicator	Graco 415	Coventional Spray (Iwata)	Short Hair Stiff Nylon Roller (Stanley)
	Graco 417		Stiff Nylon Brush
Pressure	90-120 kg/cm ²	3-4 kg/cm ²	-

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.



APPLICATION SYSTEM

Surface Preparation

Steel

: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project.

Remark : The surface must be thoroughly dry and apply the protective coating within 4 hours to cleaned surface.

Before Recoat by Topcoat

: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.

: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.

: Surface repara (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.

Coating System

Protective Coating

: **Primer & Topcoat Silguard 700 15 microns x 2 coats**

Recommendation

: The proper relative humidity in the work shall not exceed 85% RH.

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

Shelf life

: 24 months at 30-35 °C

Package

Packaging size

1 Gallon Set

1 Gallon

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.