### TOA Heavy Duty Coating Page 1 LEAD GUARD PRIMER 1120

## **Technical Data Sheet**



Rev. 1 10/2017

### FEATURES

: Lead Guard Primer 1120 is an alkyd based rust preventing primer containing zinc- phosphate pigment. : As a rust preventing primer for steel structure, deck, hold area, above water area and combination with complete alkyd system.

TECHNICAL INFORMATION							
Туре	: Alkyd Paint						
Color	: Orange						
Film appearance	: Matt						
Specific gravity	$: 1.80 \pm 0.05$						
Solid by volume	: 53 ± 2 %						
Flash point	: 32 °C						
		Minimum	Maximum	Recommended			
Dry film thickness	(Microns)	30	50	40			
Wet film thickness	(Microns)	57	94	75			
Theoretical coverage.	m <sup>2</sup> / Liter	17.7	10.6	13.3			
	m <sup>2</sup> / Gallon	66.9	40.1	50.2			
Practical coverage.	m <sup>2</sup> / Liter	16.0	9.5	12.0			
	m <sup>2</sup> / Gallon	60.2	36.0	45.0			
		Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition					
	method and technique; as well as the structure and dimensions of the object to be coated.						
	Temperature	25 °C	30 °C	35 °C			
Touch dry	Surface dry	1.5 hrs.	1 hr.	45 mins			
Recoat dry	Hard dry	10 hrs.	6 hrs.	4 hrs.			
Full cure	Minimum	10 hrs.	8 hrs.	6 hrs.			
	Maximum	-	-	-			
Potlife							
		Remark : Drying times are generally related to air circulation, temperature, film thickness and number					
	of coats, and w	ill be affected corr	espondingly.				
APPLICATION							
	Mixi	Mixing Ratio		Part B			
	Ву	By Volume		-			
	Ву	By Weight		-			
	Applica	tion Method	Airless Spray	Air Spray	Brush / Roller		
	Dil	uted by	<b>_</b>				
	TOAT	hinner 12	5-10	15-20	10-15		
	Ар	plicator	Graco 519 Graco 521	Coventional Spray (Iwata)	Short Hair Stiff Nylor Roller (Stanley) Stiff Nylon Brush		
	Pr	essure	110-140 kg/cm $^2$	3-4 kg/cm <sup>2</sup>	-		

## TOA **LEAD GUARD PRIMER 1120**

Heavy Duty Coating | Page 2

# **Technical Data Sheet**



Rev. 1 10/2017

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.

APPLICATION SYSTEM							
Surface Preparation							
Steel	Remover all o	Remover all oil, grease, dirt, oxide and other foreign material.					
	High Quality						
	: Should be bl	: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5					
	to a near-wh	to a near-white finish using a suitable abrasive.					
	Medium Quali	Medium Quality : Treatment by using Power tool cleaning in accordance with SIS St 3 or SSPC-SP3 .					
	: Treatment by						
	Remark : The	Remark : The surface must be thoroughly dry and apply the protective coating within 4 hours					
	to cleaned surface.						
Before Recoat by Topcoat	: Remover all	: Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.					
	Solvent Clea						
	: If over 7 day	: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per					
	SSPC-SP1,	Solvent Cleaning before coating.					
Coating System							
Protective Coating	: Primer	Lead Guard Primer 1120	40 microns x 2 coats				
r rotootivo coating	: Topcoat	TOA High Gloss Enamel	40 microns x 2 coats				
	. Topedat	TOA HIgh Gloss Enamer					
Recommendation	Recommendation : The proper relative humidity in the work shall not exceed 85% RH.						
i locominentation	: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air						
		temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop					
	on substrate	on substrate effective adhesion and drying time.					
	_						
HANDLING AND STORAGE							
Storage condition	: The product must be stored in accordance with national regulations. Storage conditions are to keep						
	the containers in a dry, cool, well ventilated space and away from source of heat and ignition.						
Shelf life	: 24 months at 30-35 °C						
		: The product must be stored in accordance with national regulations. Storage conditions are to keep					
	the containers in a dry, cool, well ventilated space and away from source of heat and ignition.						
	Containers n	nust be kept tightly closed.					
Package	Packagir	ng size					
	1 Gallo	on Set 1 Gallon					
HEALTH AND SAFETY							
HLALIH AND SAFELT	· Places share	no the propertioners potions -	played on the container. Use under well vertileted				
		: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediate					
		be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and					
		ention sought immediately.					
			ety hazards and precautions for use of this product,				
		he Safety Data Sheet.					
		-					

# 

Heavy Duty Coating Page 3

## LEAD GUARD PRIMER 1120

# **Technical Data Sheet**



Rev. 1 10/2017

#### DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.