

FEATURES

: TOA Vinyl Anti-Fouling Paint is a special vinyl synthetic resin paint 18 months protection as a cuprous oxide type. High content of antifoulant. High solid and give thickness film.

: As an anti-fouling paint of steel and wooden ship's bottom and under water area. It provides very effective and extended protection against fouling.

TECHNICAL INFORMATION

Type	: A Special vinyl synthetic resin.
Color	: Reddish Brown
Film appearance	: Matt
Specific gravity	: 1.58 ± 0.02
Solid by volume	: $50 \pm 2 \%$
Flash point	: 17°C

		Minimum	Maximum	Recommended
Dry film thickness	(Microns)	50	75	75
Wet film thickness	(Microns)	100	150	150
Theoretical coverage.	m ² / Liter	10.0	6.7	6.7
	m ² / Gallon	37.9	25.2	25.2
Practical coverage.	m ² / Liter	9.0	6.0	6.0
	m ² / Gallon	34.0	23.0	23.0

Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

	Temperature	25 °C	30 °C	35 °C
Touch dry	Surface dry	10 mins	8 mins	5 mins
Recoat dry	Hard dry	168 hrs	135 hrs.	85 hrs.
Full cure	Minimum	3 hrs.	2 hrs.	1 hr.
	Maximum	8 hrs.	6 hrs	4 hrs.

Remark : Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

APPLICATION

Mixing Ratio	Part A	Part B	
By Volume	1	-	
By Weight	1	-	
Application Method	Airless Spray	Air Spray	Brush / Roller
Diluted by TOA Thinner 51	5-10	15-20	15-20
Applicator	Graco 419	Coventional Spray (Iwata)	Short Hair Stiff Nylon Roller (Stanley)
	Graco 421		Stiff Nylon Brush
Pressure	120-150 kg/cm ²	3-4 kg/cm ²	-

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.

APPLICATION INFORMATION

Surface Preparation

Steel

: Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive. And/or by use the surface preparation with requirements. of the primer and/or as the Spec of the project.

Remark : The surface must be thoroughly dry and apply the protective coating within 4 hours to cleaned surface.

Before Recoat by Topcoat

: Remove all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.

: If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.

: Surface repair (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.

Coating System

Protective Coating

: Primer	Coal Tar Epoxy # 111	125 microns x 2 coats
: Undercoat	Tie Guard	40 microns x 1 coat
: Topcoat	TOA Anti-Fouling	75 microns x 2 coats

Recommendation

: The proper relative humidity in the work shall not exceed 85% RH.

: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

HANDLING AND STORAGE

Storage condition

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

Shelf life

: 24 months at 30-35 °C

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Package

Packaging size

1 Gallon Set

1 Gallon

HEALTH AND SAFETY

: Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

: For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

DISCLAIMER

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.